

SPECIFICATION SHEET

SEPIOLITE 15-30 Industrial

Composition (XRD)

Sepiolite	65% (Min. 55%)
------------------	----------------

Physical properties

Density	0.65 g/cc (Max. 0.73 g/cc)
Westinghouse water absorption	130% (Min. 100%)
Westinghouse oil absorption	60% (Min. 50%)

Particle size distribution

> 1.40 mm	Max. 12%
1.40 mm - 0.25 mm	Min. 86%
< 0.25 mm	Max. 2%